

TECHNICAL DATA SHEET – CAP
[SCHEMA TECNICA – CAPSULA]**ITEM CODE** [CODICE ARTICOLO]:
35X18IXE**COMPONENTS** [COMPONENTI]

Type of gasket [Tipo di guarnizione]

Pourer [versatore]:

//

Liner [guarnizione]:

LDPE

Density [densità]:

250 kg/m³

Materiale [Materiale]

Alloy and state aluminium
[lega e stato alluminio]:

EN AW – 8011 H14 EN573.3

Thickness [Spessore]:

0.22 mm

Interior varnish [Vernice interna]:

Epoxy phenolic laquer [Lacca epossifenolica]

Exterior varnish [Vernice esterna]:

Polyester vinyl varnish [Vernice vinilicapoliestere]


PRINTING FEATURES [CARATTERISTICHE DI STAMPA]

Litho top/side [litografia di testa/parete]:

Applicable [Applicabile]

Embossing top/side: [punzonatura testa/parete]:

Applicable [Applicabile]

DIMENSIONS [DIMENSIONI]:**PACKAGING** [IMBALLO]

Recyclable [Riciclabile]:

Yes [Sì]

Components coding [Codifica componenti]:

Aluminium [alluminio]: ALU 41
Inlay [inserto]: LDPE 4

Cap weight [Peso caps]:

2,70 g ±1%

Box weight [Peso scatola]:

9 kg ±2%

Quantity for box [Quantità per scatola]:

3250 pcs

Box dimensions [Dimensioni scatola]:

590x390x380 mm

Box type [Tipo scatola]:

Double wave cardboard [Cartone a doppia onda]

Type of pallet [tipo di pallet]:

800x1200 mm EPAL

Boxes for pallet [Scatole per pallet]:

Max 20 box [Max 20 scatole]

REGULATIONS [NORMATIVA]

The materials used are suitable pursuant to Ministerial Decree 03/21/73 and subsequent, Directive 72/02/EC, Regulation 1935/2004; EC 23/2006, Reg. (CE) 10/2011 and the relative FDA standards. The user is however required to verify the compatibility of the capsules with the product with which they come into contact, in order to guarantee the absence of chemical and organoleptic alterations.

[I materiali utilizzati sono idonei ai sensi del DM 21/03/73 e successivi, Direttiva 72/02/CE, Regolamento 1935/2004; EC 23/2006, Reg. (CE) 10/2011 e alle relative norme FDA. L'utilizzatore è comunque tenuto a verificare la compatibilità delle capsule con il prodotto con cui vengono a contatto, in modo da garantire l'assenza di alterazioni chimiche ed organolettiche]